

# Application of DICTRA in development of MCrAlX coatings

Ru Lin Peng, Linköping University, Sweden

# Acknowledgement

Dr Kang Yuan

Dr Robert Ericsson

Dr Xin-Hai Li

Mr Pimin Zhang



**SIEMENS**


KME – konsortium materialteknik för termiska energiprocesser

# OUTLINE

- Background
- Oxidation-Interdiffusion Modelling
  - Model description
  - Coating design
  - $\beta$ -layer formation
- Conclusions


# High temperature protection

- Oxidation and corrosion protection:  
e.g. MCrAlY, diffusion coatings
- Temperature reduction: TBC systems




# MCrAlY coatings

- Ni and/or Co base alloy with protective scale formers Cr and Al as well as minor additions, e.g. Y, Si, Ru.
- Oxidation resistance relies on a dense, continuous scale of Al-oxide ( $\alpha$ -alumina) formed on the coating surface
- >3.5% Al is required to maintain a continuous  $\alpha$ -alumina layer in Cr-containing alloys




# The oxidation life

- Chemical composition changes (Al-depletion) due to
  - Continued surface oxidation
  - Interdiffusion between the substrate and coating
- The oxidation life depends on resistance against Al-depletion ( $\beta$ -depletion)



- **Chemical composition profile** of Ni-15Cr-28Co-11Al-0.4Y-0.25Si on IN 792 after oxidation for 100 hrs @1100 °C





# OUTLINE

- Background
- Oxidation-Interdiffusion Modelling
  - Model description
  - Coating design
  - $\beta$ -layer formation
- Conclusions



# The oxidation-diffusion model

- Substrate-coating couple in 1D
- Each node presents a location in the couple with composition of the material at the point



# Oxidation and diffusion simulation

- DICTRA and databases from Thermo-Calc
  - Phases considered typically include  $\gamma$ ,  $\beta$ ,  $\alpha$ ,  $\gamma'$
- Surface oxidation induced Al-depletion, derived from TGO thickness,  $h$


$$h = h_0 + (kt)^{1/n}$$

- Diffusion

✓ Upper bound diffusion:  $D^{eff} = \sum f^i D^i$

✓ Lower bound diffusion:  $D^{eff} = D^i + \frac{f^i}{\frac{1}{D^j - D^i} + \frac{f^j}{3D^i}}$


# Simulated $\beta$ -depletion



- Good agreement with observed microstructural change


Kang et al. Surface & Coatings Technology 232 (2013) 204–215

# Simulated chemical composition profiles



- Changes in chemical composition profiles were captured

## Other composition profiles



# OUTLINE

- Background
- Oxidation-Interdiffusion Modelling
  - Model description
  - Coating design
  - $\beta$ -layer formation
- Conclusions

# Simulation set-up

- Varied composition in coating: Cr, Co, and Al
- Varied composition in substrate: Al
- Surface oxidation, derived from TGO thickness

$$h = (kt)^{1/2} \text{ where } k = k_0 e^{-\frac{Q}{RT}}$$

$$k_0 = 3.20 \cdot 10^4 \mu m^2/h; Q = 1.45 \cdot 10^5 \text{ J/mol}$$



- Oxidation Life Criterion
  - Time to complete  $\beta$  depletion
- Cr-equivalent

$$Cr_e = Cr + 0.5Co$$



Ericsson et al. Surface & Coatings Technology 253 (2014) 27–37

# Oxidation life

Substrate  
0.5%Al



Substrate  
5%Al



- A stronger effect of increasing coating's Al on high Al substrate: 3 to 8 times for 0.5% Al substrate against 3 to 30 times for 5% Al substrate
- The influence of substrate Al is larger at higher oxidation temperature.





# OUTLINE

- Background
- Oxidation-Interdiffusion Modelling
  - Model description
  - Coating design
  - $\beta$ -layer formation
- Conclusions

# A continuous $\beta$ -layer formed after TCF test

100-1100 °C for ~300 cycles





- The  $\beta$ -layer corresponds to Al accumulation at coating-substrate interface

	Ni	Co	Cr	Al	Y	Si	Ta	Ti	Mo	W	Re
Coat-1	50.3	22.2	14.7	11.4	0.1	0.3	1.0	-	-	-	-
CMSX-4	59.3	9.6	6.3	5.5	-	-	7.0	1.0	0.6	6.6	4.0


Kang et al. Journal of Thermal Spray Technology, Volume 25(1-2), 2016, 244-251

# Modelling resolut



- Simulation using the lower bound diffusion module predicts the formation of the  $\beta$ -layer.
- The characteristic layered microstructure were also predicted, except for the extra  $\gamma$ -zone between the  $\beta$  and  $\gamma + \beta$  zones.

# Composition for the formation of $\beta$ -layer



c1 to c5

MCrAlY coatings

s1 to s11

Superalloy substrates

- Critical Al-activity in the coating and substrate
- Substrate of high Al activity has a low sinking effect on Al
- Cr, Ta, Mo and Re can increase the Al-activity

# Conclusions

- Interdiffusion plays an important role in the oxidation behavior of MCrAlY-superalloy systems.
- The effect of interdiffusion on oxidation life is dependent on temperature and composition of the coating and substrate.
- The simulations indicate the potential and possibility of enhancing oxidation resistance of MCrAlY-superalloy systems by matching coatings to substrate alloys.
- DICTRA is a powerful computational tool in metallic coating development and life modelling.

Thanks you for your attention!

[www.liu.se](http://www.liu.se)